

Data Sheet

High Speed, Low Loss Multi-layer Materials

Halogen-free
MEGTRON2

Laminate R-1577
Prepreg R-1570

Jun. 2017 No.17061634

Specification / Laminate R-1577

Property		Units	Test Method	Condition	Value	
THERMAL	Glass Transition Temp (Tg)	°C	DSC	As received	170	
			TMA	As received	165	
			DMA	As received	190	
	Thermal Decomposition Temp (Td)		°C	TGA	As received	380
	Time to Delam (T288)	Without Cu	min	IPC TM-650 2.4.24.1	As received	> 120
		With Cu	min	IPC TM-650 2.4.24.1	As received	25
	CTE : $\alpha 1$	X - axis	ppm / °C	IPC TM-650 2.4.24	< Tg	14 - 16
		Y - axis	ppm / °C	IPC TM-650 2.4.24	< Tg	14 - 16
		Z - axis	ppm / °C	IPC TM-650 2.4.24	< Tg	34
CTE : $\alpha 2$	Z - axis	ppm / °C	IPC TM-650 2.4.24	> Tg	200	
ELECTRICAL	Volume Resistivity		M Ω - cm	IPC TM-650 2.5.17.1	C-96/35/90	1 x 10 ⁹
	Surface Resistivity		M Ω	IPC TM-650 2.5.17.1	C-96/35/90	1 x 10 ⁸
	Dielectric Constant (Dk)	@ 1MHz	-	IPC TM-650 2.5.5.9	C-24/23/50	4.3
		@ 1GHz	-	IPC TM-650 2.5.5.9	C-24/23/50	4.1
	Dissipation Factor (Df)	@ 1MHz	-	IPC TM-650 2.5.5.9	C-24/23/50	0.009
		@ 1GHz	-	IPC TM-650 2.5.5.9	C-24/23/50	0.010
PHYSICAL	Water Absorption		%	IPC TM-650 2.6.2.1	D-24/23	0.14
	Peel Strength	1oz	kN / m	IPC TM-650 2.4.8	As Received	1.3
	Flammability		-	UL	C-48/23/50	94V-0

Sample thickness ; 32 mil (0.8 mm)

*The data above show actual values and are not guaranteed.

Specification / Laminate R-1577

1MHz - 1GHz ; IPC TM650-2.5.5.9

Nominal Thickness		Cloth Style	Typical Resin Content	Typical Dk			Typical Df		
mil	mm			1MHz	100MHz	1GHz	1MHz	100MHz	1GHz
2.0	0.05	106 x 1	72%	3.97	3.83	3.80	0.011	0.011	0.011
2.5	0.06	1080 x 1	59%	4.26	4.13	4.10	0.009	0.010	0.010
3.0	0.08	1080 x 1	64%	4.14	4.01	3.98	0.010	0.010	0.011
3.5	0.09	3313 x 1	53%	4.41	4.29	4.26	0.009	0.009	0.010
4.0	0.10	3313 x 1	57%	4.30	4.18	4.14	0.009	0.010	0.010
	0.10	106 x 2	72%	3.97	3.83	3.80	0.011	0.011	0.011
4.1	0.10	2116 x 1	46%	4.60	4.50	4.47	0.008	0.009	0.009
4.5	0.11	2116 x 1	52%	4.43	4.32	4.29	0.009	0.009	0.010
5.0	0.13	2116 x 1	56%	4.33	4.21	4.18	0.009	0.010	0.010
	0.13	1080 x 2	59%	4.26	4.13	4.10	0.009	0.010	0.010
5.1	0.13	1504 x 1	42%	4.72	4.62	4.59	0.008	0.008	0.009
6.0	0.15	1080 x 2	64%	4.14	4.01	3.98	0.010	0.010	0.011
		1078 x 2	64%	4.14	4.01	3.98	0.010	0.010	0.011
6.1	0.15	1501 x 1	45%	4.63	4.53	4.50	0.008	0.009	0.009
8.0	0.20	7628 x 1	47%	4.57	4.46	4.43	0.008	0.009	0.009
	0.20	3313 x 2	56%	4.33	4.21	4.18	0.009	0.010	0.010
8.1	0.20	2116 x 2	46%	4.60	4.50	4.47	0.008	0.009	0.009
10.0	0.25	2116 x 2	57%	4.30	4.18	4.14	0.009	0.010	0.010
12.0	0.30	1501 x 2	45%	4.63	4.53	4.50	0.008	0.009	0.009
16.0	0.40	7628 x 2	47%	4.57	4.46	4.43	0.008	0.009	0.009
20.0	0.50	7628 x 2 + 2116 x 1	47%	4.57	4.46	4.43	0.008	0.009	0.009

*The data above show actual values and are not guaranteed.

Specification / Laminate R-1577

2GHz-10GHz ; IPC TM650-2.5.5.5

Nominal Thickness		Cloth Style	Typical Resin Content	Typical Dk					Typical Df				
mil	mm			2GHz	4GHz	6GHz	8GHz	10GHz	2GHz	4GHz	6GHz	8GHz	10GHz
2.0	0.05	106 x 1	72%	3.78	3.77	3.76	3.74	3.72	0.012	0.013	0.014	0.014	0.015
2.5	0.06	1080 x 1	59%	4.08	4.07	4.06	4.04	4.02	0.011	0.012	0.012	0.013	0.013
3.0	0.08	1080 x 1	64%	3.95	3.95	3.94	3.92	3.90	0.011	0.012	0.013	0.013	0.014
3.5	0.09	3313 x 1	53%	4.23	4.23	4.22	4.20	4.18	0.010	0.011	0.012	0.012	0.013
4.0	0.10	3313 x 1	57%	4.13	4.12	4.11	4.09	4.08	0.010	0.012	0.012	0.013	0.013
	0.10	106 x 2	72%	3.78	3.77	3.76	3.74	3.72	0.012	0.013	0.014	0.014	0.015
4.1	0.10	2116 x 1	46%	4.44	4.43	4.42	4.41	4.39	0.009	0.010	0.011	0.011	0.012
4.5	0.11	2116 x 1	52%	4.26	4.25	4.25	4.23	4.21	0.010	0.011	0.012	0.012	0.013
5.0	0.13	2116 x 1	56%	4.15	4.14	4.14	4.12	4.10	0.010	0.011	0.012	0.013	0.013
	0.13	1080 x 2	59%	4.08	4.07	4.06	4.04	4.02	0.011	0.012	0.012	0.013	0.013
5.1	0.13	1504 x 1	42%	4.57	4.56	4.55	4.54	4.52	0.009	0.010	0.011	0.011	0.012
6.0	0.15	1080 x 2	64%	3.95	3.95	3.94	3.92	3.90	0.011	0.012	0.013	0.013	0.014
		1078 x 2	64%	3.95	3.95	3.94	3.92	3.90	0.011	0.012	0.013	0.013	0.014
6.1	0.15	1501 x 1	45%	4.47	4.46	4.45	4.44	4.42	0.009	0.010	0.011	0.012	0.012
8.0	0.20	7628 x 1	47%	4.41	4.40	4.39	4.38	4.36	0.010	0.011	0.011	0.012	0.012
	0.20	3313 x 2	56%	4.15	4.14	4.14	4.12	4.10	0.010	0.011	0.012	0.013	0.013
8.1	0.20	2116 x 2	46%	4.44	4.43	4.42	4.41	4.39	0.009	0.010	0.011	0.011	0.012
10.0	0.25	2116 x 2	57%	4.13	4.12	4.11	4.09	4.08	0.010	0.012	0.012	0.013	0.013
12.0	0.30	1501 x 2	45%	4.47	4.46	4.45	4.44	4.42	0.009	0.010	0.011	0.012	0.012
16.0	0.40	7628 x 2	47%	4.41	4.40	4.39	4.38	4.36	0.010	0.011	0.011	0.012	0.012
20.0	0.50	7628 x 2 + 2116 x 1	47%	4.41	4.40	4.39	4.38	4.36	0.010	0.011	0.011	0.012	0.012

*The data above show actual values and are not guaranteed.

Specification / Prepreg R-1570

1MHz - 1GHz ; IPC TM650-2.5.5.9

Cloth Style	Typical Resin Content	Typical Thickness (um)	Typical Dk			Typical Df		
			1MHz	100MHz	1GHz	1MHz	100MHz	1GHz
1037	77%	59	3.85	3.70	3.67	0.011	0.012	0.012
106	68%	43	4.05	3.92	3.89	0.010	0.011	0.011
	72%	50	3.97	3.83	3.80	0.011	0.011	0.011
	76%	59	3.89	3.75	3.72	0.011	0.012	0.012
1067	67%	52	4.07	3.94	3.91	0.010	0.011	0.011
	71%	61	3.99	3.85	3.82	0.011	0.011	0.011
1080	65%	74	4.12	3.98	3.95	0.010	0.011	0.011
	69%	86	4.03	3.89	3.86	0.010	0.011	0.011
	73%	100	3.95	3.81	3.78	0.011	0.011	0.012
1078	64%	74	4.14	4.01	3.98	0.010	0.010	0.011
	68%	84	4.05	3.92	3.89	0.010	0.011	0.011
3313	58%	105	4.28	4.16	4.13	0.009	0.010	0.010
	64%	125	4.14	4.01	3.98	0.010	0.010	0.011
2116	55%	123	4.35	4.23	4.20	0.009	0.010	0.010
	58%	133	4.28	4.16	4.13	0.009	0.010	0.010
1504	51%	158	4.46	4.35	4.32	0.009	0.009	0.009
1501	51%	176	4.46	4.35	4.32	0.009	0.009	0.009
7628	48%	207	4.54	4.43	4.40	0.008	0.009	0.009
	51%	223	4.46	4.35	4.32	0.009	0.009	0.009
	54%	241	4.38	4.26	4.23	0.009	0.009	0.010

*The data above show actual values and are not guaranteed.

Specification / Prepreg R-1570

2GHz-10GHz ; IPC TM650-2.5.5.5

Cloth Style	Typical Resin Content	Typical Thickness (um)	Typical Dk					Typical Df				
			2GHz	4GHz	6GHz	8GHz	10GHz	2GHz	4GHz	6GHz	8GHz	10GHz
1037	77%	59	3.65	3.64	3.63	3.61	3.58	0.012	0.013	0.014	0.015	0.015
106	68%	43	3.86	3.85	3.85	3.83	3.81	0.011	0.013	0.013	0.014	0.014
	72%	50	3.78	3.77	3.76	3.74	3.72	0.012	0.013	0.014	0.014	0.015
	76%	59	3.70	3.69	3.68	3.66	3.60	0.012	0.013	0.014	0.015	0.015
1067	67%	52	3.89	3.88	3.87	3.85	3.83	0.011	0.012	0.013	0.014	0.014
	71%	61	3.80	3.79	3.78	3.77	3.74	0.011	0.013	0.014	0.014	0.015
1080	65%	74	3.93	3.92	3.91	3.90	3.88	0.011	0.012	0.013	0.014	0.014
	69%	86	3.84	3.83	3.82	3.80	3.79	0.011	0.013	0.013	0.014	0.014
	73%	100	3.76	3.75	3.74	3.72	3.70	0.012	0.013	0.014	0.014	0.015
1078	64%	74	3.95	3.95	3.94	3.92	3.90	0.011	0.012	0.013	0.013	0.014
	68%	84	3.86	3.85	3.85	3.83	3.81	0.011	0.013	0.013	0.014	0.014
3313	58%	105	4.10	4.09	4.08	4.07	4.05	0.010	0.012	0.012	0.013	0.013
	64%	125	3.95	3.95	3.94	3.92	3.90	0.011	0.012	0.013	0.013	0.014
2116	55%	123	4.18	4.17	4.16	4.15	4.13	0.010	0.011	0.012	0.013	0.013
	58%	133	4.10	4.09	4.08	4.07	4.05	0.010	0.012	0.012	0.013	0.013
1504	51%	158	4.29	4.28	4.27	4.26	4.24	0.010	0.011	0.012	0.012	0.012
1501	51%	176	4.29	4.28	4.27	4.26	4.24	0.010	0.011	0.012	0.012	0.012
7628	48%	207	4.38	4.37	4.36	4.35	4.33	0.010	0.011	0.011	0.012	0.012
	51%	223	4.29	4.28	4.27	4.26	4.24	0.010	0.011	0.012	0.012	0.012
	54%	241	4.21	4.20	4.19	4.17	4.16	0.010	0.011	0.012	0.012	0.013

*The data above show actual values and are not guaranteed.

++ Before purchase ++

【Notes before you use】

- Prior to adoption and use of a product contained in the datasheet, please verify the suitability for your application by your quality testing, evaluation, etc.
- We would like to have a delivery specifications mutually agreed for the product that you have decided to use. The agreements defined in the delivery specifications are assigned higher priority.
- Please note that images shown may somewhat differ from the actual product in color.
- Please note that specifications and external design are subject to change for product improvement without notice.
- For details on products in the datasheet, please contact your distributor or our sales department.

【Safety Information】

- Before using the product, please read the delivery specifications carefully or contact the distributor from which you purchased the product or our sales department in order to use the product correctly.
- The products in the datasheet are Electronic circuit board materials for electronic and electrical devices. Please do not use them for other than specified use.

Please Contact us of more

【Technical Marketing】

- Japan (Osaka) TEL: 81-6-6904-2771
- USA (Cupertino) TEL: 1-408-861-3946
- Austria (Enns) TEL: 43-7223-883
- China (Guangzhou) TEL: 86-20-8713-0888

【Sales Offices】

- China (Hong Kong) TEL: 852-2529-3956
- China (Suzhou) TEL: 86-512-6825-1565
- China (Guangzhou) TEL: 86-20-8713-0888
- Korea (Seoul) TEL: 82-2-361-7873
- Taiwan (Hsinchu) TEL: 886-3-598-3201
- Thailand (Ayuthaya) TEL: 66-3533-0846
- Singapore (Bedok) TEL: 65-6241-6754
- Austria (Enns) TEL: 43-7223-883
- USA (Cupertino) TEL: 1-408-861-3946
- Japan (Osaka) TEL: 81-6-6904-2771

Panasonic Corporation
 Automotive & Industrial Systems Company
 Electronic Materials Business Division
 Circuit Board Materials Business Unit.
 Head Office: 1006 Kadoma, Kadoma City, Osaka 571-8506
 TEL: 81-6-6908-1101
industrial.panasonic.com/ww/electronic-materials